

## OK Autrod 13.28

A copper coated, Ni-alloyed (2,4% Ni), solid wire for GMAW of low-alloyed and low temperature steels in applications such as vessels, pipes and in the offshore industry with a minimum yield strength less than 470 Mpa. The wire provides a good impact toughness down to -60°C.

Specifications	
<b>Classifications</b>	EN ISO 14341-A : G 46 6 M21 2Ni2 EN ISO 14341-A : G 2Ni2 SFA/AWS A5.28 : ER80S-Ni2
<b>Approvals</b>	CE : EN 13479 DNV-GL : V YMS (M21) UKCA : EN 13479 VdTÜV : 06852

Approvals are based on factory location. Please contact ESAB for more information.

<b>Alloy Type</b>	Low alloyed (2.5 % Ni)
<b>Shielding Gas</b>	M21 (EN ISO 14175)

Typical Tensile Properties			
Condition	Yield Strength	Tensile Strength	Elongation
<b>EN Ar/20CO2 (M21)</b>			
As Welded	540 MPa	630 MPa	28 %
<b>AWS Ar/1-5O2 (M13)</b>			
Stress Relieved 1 hour(s) 620 °C	540 MPa	630 MPa	29 %

Typical Charpy V-Notch Properties		
Condition	Testing Temperature	Impact Value
<b>EN Ar/20CO2 (M21)</b>		
As Welded	0 °C	130 J
As Welded	-40 °C	100 J
As Welded	-60 °C	60 J
<b>AWS Ar/1-5O2 (M13)</b>		
Stress Relieved 1 hour(s) 620 °C	0 °C	162 J
Stress Relieved 1 hour(s) 620 °C	-29 °C	168 J
Stress Relieved 1 hour(s) 620 °C	-62 °C	131 J

Typical Weld Metal Analysis %									
C	Mn	Si	S	P	Ni	Cr	Mo	V	Al
0.1	1	0.4	0.01	0.01	2.4	0.05	0.1	0.001	0.01

Typical Weld Metal Analysis %	
Cu	Ti+Zr
0.15	0.05

Typical Wire Composition %			
C	Mn	Si	Ni
0.08	1.04	0.53	2.36

## OK Autrod 13.28

Deposition Data				
Diameter	Current	Voltage	Wire Feed Speed	Deposition Rate
1.0 mm	80-280 A	18-28 V	2.7-14.7 m/min	1.0-5.4 kg/h
1.2 mm	120-350 A	20-33 V	2.7-12.4 m/min	1.5-6.6 kg/h